

DELAPHOS

TECHNICAL DATA SHEET DELAPHOS ZINC PHOSPHATE

Zinc Phosphate is hydrated. It has a number of molecules of water associated with each molecule of Zinc Phosphate in the crystal structure. Delaphos is supplied as the Dihydrate form (Delaphos 2, 2M) or the Tetrahydrate form (Delaphos 4).

USES

Anti-corrosive paint primer systems, especially those based on solvent borne Epoxy-Polyamide, Chlorinated rubber, Alkyd and Polyurethane resins. Also effective in waterbased systems.

<u>PHYSICAL PROPERTIES</u>	<u>Delaphos 2M</u>	<u>Delaphos 2</u>	<u>Delaphos 4</u>	<u>TEST METHOD</u>
Loss on Ignition	8.50 – 10.00%	8.50 – 10.00%	10.00 - 15.00%	ISO 6745
Zn content after ignition	50.5 – 52.0%	50.5 – 52.0%	50.5 – 52.0%	ISO 6745
Resistance of aq. Extract	>6500 ohm-cm	>6500 ohm-cm	>6500 ohm-cm	ISO 787/14 modified
PH of aq. Extract	6 – 8	6-8	6 – 8	ISO 787/9 modified
Solubility in water	< 0.1%	< 0.1%	< 0.1%	ISO 787/8
Specific gravity	3.1 g/cc	3.1 g/cc	3.1 g/cc	ISO 787/10
Bulk density (typ.)	1.1 g/cc	1.1 g/cc	1.1 g/cc	ISO 787/11
Retention of 45µm sieve	< 0.01%	< 0.3%	< 0.3%	ISO 787/7
Oil absorption	20 –24g/100g	20 –24g/100g	20 –24g/100g	ISO 787/5
Mean particle size	7.5µm	8.0µm	8.0µm	Coulter laser diffraction

PLEASE NOTE

Health Safety and Environmental information should be considered when using this product. A specific Material Safety Data Sheet is available from JPE Holdings Ltd

BS5193

Conforms to

Issue 4/2009